

Technical Data Sheet

***Polyvin* 6040DC-2169 FORD BLK**



Polyvinyl Chloride, Unspecified

Product Description

Low Gloss PVC 55A

Processing Method Injection Molding

Attribute Low Gloss

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density - Specific Gravity	1.26	g/cm ³	ASTM D792
Mechanical			
Tensile Strength at Yield, (500 mm/min)	10.0	MPa	ASTM D638
Tensile Elongation at Break, (500 mm/min)	350	%	ASTM D638
Tear Strength, (500 mm/min)	30.0	kN/m	ASTM D624
Hardness			
Durometer Hardness, (Shore A, 15 sec)	55		ASTM D2240