

## Technical Data Sheet

**Solef**PVDF 3108/0903 BLK(TOL)

Polyvinylidene Fluoride

**Product Description**

Anti-static - Injection

**Processing Method** Injection Molding

<b>Typical Properties</b>	<b>Nominal Value</b>	<b>Units</b>	<b>Test Method</b>
<b>Physical</b>			
Melt Volume Flow Rate			
(230 °C/2.16 kg)	1.0	cm <sup>3</sup> /10 min	ISO 1133
(230 °C/5.0 kg)	4.0	cm <sup>3</sup> /10 min	ISO 1133
Density, (Method A)	1.78	g/cm <sup>3</sup>	ISO 1183
<b>Mechanical</b>			
Tensile Stress at Yield, (Type 1A, 50 mm/min)	55.0	MPa	ISO 527-2
Flexural Modulus, (2.0 mm/min)	2750	MPa	ISO 178
Tensile Strain at Yield, (Type 1A, 50 mm/min)	3.6	%	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	2900	MPa	ISO 527-1
Flexural Stress			
(2.0 mm/min, 3.5%)	72.0	MPa	ISO 178
(2.0 mm/min, 6.0%)	85.0	MPa	ISO 178
<b>Impact</b>			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	7.0	kJ/m <sup>2</sup>	ISO 179
Charpy Impact Strength - Unnotched, (23 °C, Type 1, Edgewise)	No Break		ISO 179
<b>Hardness</b>			
Shore Hardness, (Shore D, 3 sec)	81		ISO 868
<b>Thermal</b>			
Vicat Softening Temperature			
(B (50N), 50 °C/h)	147	°C	ISO 306
(A (10N), 50 °C/h)	171	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	138	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	85.0	°C	ISO 75-2/A
<b>Electrical</b>			
Thermal Conductivity	0.33	W/m/K	ISO 22007-2
Volume Resistivity at 4 pole electrode	<1000	ohm*cm	
<b>Flammable</b>			

Glow Wire Flammability Index		
(1.5 mm)	960 °C	IEC 60695-2-12
(3.0 mm)	960 °C	IEC 60695-2-12
Glow Wire Ignition Temperature		
(1.5 mm)	900 °C	IEC 60695-2-13
(3.0 mm)	900 °C	IEC 60695-2-13
<b>UL Information</b>		
Flame Rating		
(1.6 mm)	V-0	UL 94
(3.2 mm)	V-0	UL 94
Flammability Classification		
(1.6 mm)	V-0	IEC 60695-11-10, -20
(3.2 mm)	V-0	IEC 60695-11-10, -20