

Technical Data Sheet

Accutech SAN930G20L

Styrene Acrylonitrile
LyondellBasell Industries
Engineering Plastics

General

- | | |
|------------------------|-------------------------------------|
| Filler / Reinforcement | • Glass Fiber, 20% Filler by Weight |
| Forms | • Pellets |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.21	1.21 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 Kg)	3.0 g/10 min	3.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	725000 psi	5000 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	13200 psi	91.0 MPa	
Break	13200 psi	91.0 MPa	
Tensile Elongation			ASTM D638
Yield	3.0 %	3.0 %	
Break	4.0 %	4.0 %	
Flexural Modulus	1.04E+6 psi	7200 MPa	ASTM D790
Flexural Strength	17800 psi	123 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.82 ft·lb/in	44 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	118	118	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	234 °F	112 °C	
264 Psi (1.8 Mpa), Unannealed	208 °F	98.0 °C	

Notes

These are typical property values not to be construed as specification limits.