

Technical Data Sheet

Accutech SAN930G30L

Styrene Acrylonitrile
LyondellBasell Industries
Engineering Plastics

General			
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.28	1.28 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 Kg)	3.0 g/10 min	3.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	928000 psi	6400 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	13800 psi	95.0 MPa	
Break	13800 psi	95.0 MPa	
Tensile Elongation			ASTM D638
Yield	2.0 %	2.0 %	
Break	3.0 %	3.0 %	
Flexural Modulus	1.45E+6 psi	10000 MPa	ASTM D790
Flexural Strength	19100 psi	132 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.84 ft·lb/in	45 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	118	118	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	216 °F	102 °C	
264 Psi (1.8 Mpa), Unannealed	207 °F	97.0 °C	

Notes

These are typical property values not to be construed as specification limits.