

Technical Data Sheet

Ronfalin SAN 4405 FC

Styrene Acrylonitrile
LyondellBasell Industries
Engineering Plastics

Product Description

Good flow SAN grade with high chemical resistance and food contact approvals. (Former name: POLYMAN SAN 29/10 K3005)

General

Processing Method	• Injection Molding
Resin ID (ISO 1043)	• SAN

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.08 g/cm ³	1.08 g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR)			ISO 1133
220°C/10.0 Kg	25 cm ³ /10min	25 cm ³ /10min	
230°C/3.8 Kg	10 cm ³ /10min	10 cm ³ /10min	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	537000 psi	3700 MPa	ISO 527-1/1A/1
Tensile Stress (Break)	10200 psi	70.0 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.0 %	3.0 %	ISO 527-2/1A/5
Flexural Modulus ¹	508000 psi	3500 MPa	ISO 178
Flexural Stress ¹ (3.0% Strain)	15200 psi	105 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength	1.4 ft·lb/in ²	3.0 kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	8.1 ft·lb/in ²	17 kJ/m ²	ISO 179/1eU
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness (H 358/30)	24800 psi	171 MPa	ISO 2039-1
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	217 °F	103 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	212 °F	100 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	216 °F	102 °C	ISO 306/B50
--	223 °F	106 °C	ISO 306/A50
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index	600 V	600 V	IEC 60112
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 In (1.5 Mm)	HB	HB	
0.12 In (3.0 Mm)	HB	HB	

Additional Information

1.) Not for use in medical or pharmaceutical applications

Technical Data Sheet

Ronfalin SAN 4405 FC

Styrene Acrylonitrile
LyondellBasell Industries
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Processing (Melt) Temp	428 to 482 °F	220 to 250 °C
Mold Temperature	122 to 176 °F	50 to 80 °C

Notes

¹ 0.079 in/min (2.0 mm/min)

Notes

These are typical property values not to be construed as specification limits.