

Technical Data Sheet
DuraGrip® DGR 6830NC
 Thermoplastic Elastomer
 Engineering Plastics



Product Description

DuraGrip® 6830NC is an FDA compliant Thermoplastic Elastomer (TPE) that is easy to use in injection molding and extrusion processes. DuraGrip® 6830NC has an excellent soft touch feel, good elasticity, will bond to polypropylene and some polyethylenes. It complies with 21 C.F.R.177.2600 and 21 C.F.R. 177.1210 (non-fatty/non-oily foodstuffs). DuraGrip® 6830NC is not hygroscopic and under normal conditions does not require drying.

General

Features	• Good Adhesion		
Agency Ratings	• EU 2002/96/EC (WEEE)	• FDA 21 CFR 177.1210	• FDA 21 CFR 177.2600
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity			
--	0.975	0.973 g/cm ³	ASTM D792
--	0.973 g/cm ³	0.973 g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/5.0 kg)	16 g/10 min	16 g/10 min	ASTM D1238

Elastomers	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress			ASTM D412 ISO 37
100% Strain	160 psi	1.10 MPa	
300% Strain	225 psi	1.55 MPa	
Tensile Strength (Yield)	650 psi	4.48 MPa	ASTM D412 ISO 37
Tensile Elongation (Break)	750 %	750 %	ASTM D412 ISO 37
Tear Strength ¹	75.0 lbf/in	13.1 kN/m	ASTM D624


Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore A, 5 sec)	32	32	ASTM D2240 ISO 868

Fill Analysis	Nominal Value (English)	Nominal Value (SI)	Test Method
Melt Viscosity (374°F (190°C), 200 sec ⁻¹)	172 Pa·s	172 Pa·s	ASTM D3835

Additional Information

The value listed as Density -Specific Gravity, ASTM D792, was tested in accordance with ASTM D471.
 The value listed as Density, ISO 1183, was tested in accordance with ISO 2781.

Technical Data Sheet
DuraGrip® DGR 6830NC
 Thermoplastic Elastomer
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Rear Temperature	370 to 390 °F	188 to 199 °C
Middle Temperature	390 to 410 °F	199 to 210 °C
Front Temperature	420 to 440 °F	216 to 227 °C
Nozzle Temperature	400 to 430 °F	204 to 221 °C
Processing (Melt) Temp	390 to 430 °F	199 to 221 °C
Mold Temperature	110 to 130 °F	43 to 54 °C
Screw Speed	25 to 100 rpm	25 to 100 rpm

Injection Notes

- Injection Speed: 1 to 3 in³/sec
- Injection Time (1st Stage/Boost): 0.5 to 4 sec
- Second Stage Pressure: 150 to 300 psi
- Second Stage Time: 3 to 10 sec
- Cooling Time: 10 to 20 sec
- Back Pressure: 20 to 75 %