

## Technical Data Sheet

**DuraGrip DGR-6030NCNAT**

Thermoplastic Elastomer

**Product Description**

*DuraGrip* DGR 6030NC is designed to be a general-purpose Thermoplastic Elastomer (TPE) that is easy to use in an injection molding process. DGR 6030NC has an excellent soft touch feel, will bond to olefinics, and is easy to color. *DuraGrip* is not hygroscopic and under normal conditions does not require drying.

<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Good Colorability
<b>Forms</b>	Pellets
<b>Application</b>	General Purpose

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Density	0.988	g/cm <sup>3</sup>	ISO 1183
Density - Specific Gravity	0.988	g/cm <sup>3</sup>	ASTM D792
Change in Volume			
(in ASTM #1 Oil, 100 °C, 168 hr)	6.0	%	ISO 1817
(in ASTM #1 Oil, 100 °C, 168 hr)	6.0	%	ASTM D471
(in IRM 903 Oil, 100 °C, 168 hr)	70	%	ASTM D471
(in IRM 903 Oil, 100 °C, 168 hr)	70	%	ISO 1817
(in Water, 100 °C, 168 hr)	-9.0	%	ISO 1817
(in Water, 100 °C, 168 hr)	-9.0	%	ASTM D471
(in Reference Fuel B, 24 °C, 168 hr)	22	%	ISO 1817
(in Reference Fuel B, 24 °C, 168 hr)	22	%	ASTM D471
Melt Viscosity, (190 °C, 300 sec <sup>-1</sup> )	129	Pa·s	ASTM D3835
<b>Mechanical</b>			
Change in Ultimate Elongation in Air			
(70 °C, 168 hr)	3.0	%	ASTM D573
(100 °C, 168 hr)	-3.0	%	ASTM D573
Tensile Stress at 100%	1.05	MPa	ASTM D412
(23 °C)	1.05	MPa	ISO 37

<b>Change in Tensile Strength in Air</b>		
(70 °C, 168 hr)	-3.0 %	ISO 188
(70 °C, 168 hr)	-3.0 %	ASTM D573
(70 °C, 168 hr, 100%)	-6.0 %	ISO 188
(70 °C, 168 hr, 100%)	-6.0 %	ASTM D573
(100 °C, 168 hr)	-9.0 %	ASTM D573
(100 °C, 168 hr)	-9.0 %	ISO 188
(100 °C, 168 hr, 100%)	-2.0 %	ASTM D573
(100 °C, 168 hr, 100%)	-2.0 %	ISO 188
Tensile Set, (100%)	5 %	ASTM D412
Tensile Strength at Yield, (23 °C)	4.38 MPa	ASTM D412
Tensile Stress at Yield, (23 °C)	4.38 MPa	ISO 37
<b>Change in Tensile Strain at Break</b>		
(168 hr, 70 °C)	3.0 %	ISO 1817
(168 hr, 100 °C)	-3.0 %	ISO 1817
Tensile Strain at Break, (23 °C)	500 %	ISO 37
Tensile Elongation at Break	500 %	ASTM D412
Tear Strength, (24 °C, Die C)	14.2 kN/m	ASTM D624
<b>Impact</b>		
Ductile/Brittle Transition Temperature	-67.2 °C	ASTM D746
<b>Hardness</b>		
Shore Hardness, (Shore A, 5 sec)	33	ISO 868
Durometer Hardness, (Shore A, 5 sec)	33	ASTM D2240
<b>Additional Information</b>		
<b>Compression Set</b>		
(24 °C, 22 hr, Method B)	10 %	ASTM D395
(100 °C, 22 hr, Method B)	53 %	ASTM D395
(24 °C, 22 hr)	10 %	ISO 815
(100 °C, 22 hr)	53 %	ISO 815
(70 °C, 22 hr, Method B)	33 %	ASTM D395
(70 °C, 22 hr)	33 %	ISO 815
Taber Abrasion Resistance, (CS-17 Wheel, 1.0E+6 g, 1000 Cycles)	140 mg	ASTM D1044

<b>Injection Parameters</b>	<b>Nominal Value</b>	<b>Units</b>
Drying Time	3	hr
Drying Temperature	66	°C
Nozzle Temperature	204 to 221	°C
Screw Speed	25 to 100	rpm
Processing (Melt) Temp	199 to 221	°C
Front Temperature	216 to 227	°C
Middle Temperature	199 to 210	°C
Rear Temperature	188 to 199	°C
Mold Temperature	43 to 54	°C
Injection Pressure	1.03 to 4.14	MPa