



## Dexflex 992

### Advanced Polyolefin

#### Product Description

Dexflex 992 very high melt flow, low flexural modulus, thermoplastic elastomeric olefin has an excellent balance of properties.

#### Product Characteristics

**Status** Commercial: Restricted

**Test Method used** ISO

**Availability** North America

**Processing Methods** Injection Molding

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	32	g/10 min
Density	ISO 1183	0.90	g/cm <sup>3</sup>
<b>Mechanical</b>			
Tensile Strain at Break	ISO 527-1, -2	>500	%
Flexural modulus	ISO 178	179	MPa
<b>Thermal</b>			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	55	°C
<b>Additional Information</b>			
Mold shrinkage	ISO 294-4		
<i>Note:</i> Please contact LyondellBasell for shrinkage recommendations.			

#### Notes

Typical properties; not to be construed as specifications.