



## Hifax 7430 XEP

### Advanced Polyolefin

#### Product Description

Hifax 7430 XEP is a reactor TPO (thermoplastic polyolefin) manufactured using LyondellBasell's proprietary *Catalloy* process technology.

It is a high melt flow, medium-high flexural modulus, highly crystalline copolymer with good balance of impact and stiffness. It is primarily used in interior trim applications requiring low temperature high speed impact performance. It is also used as a component in compounded materials for automotive and industrial applications.

The grade is available in natural pellet form.

For regulatory compliance information see *Hifax 7430 XEP Product Stewardship Bulletin (PSB)*.

#### Product Characteristics

<b>Status</b>	Commercial: Active
<b>Test Method used</b>	ISO
<b>Availability</b>	North America, Latin America
<b>Processing Methods</b>	Injection Molding
<b>Features</b>	Low Temperature Impact Resistance, Good Stiffness
<b>Typical Customer Applications</b>	Automotive Parts, Interior Applications

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Density (Method A)	ISO 1183	0.89	g/cm <sup>3</sup>
Melt flow rate (MFR) (230 °C/ 2.16 kg)	ISO 1133	18.5	g/10 min
<b>Mechanical</b>			
Tensile Stress at Break (23 °C, 50 mm/min)	ISO 527-1, -2	14	MPa
Tensile Stress at Yield (23 °C, 50 mm/min)	ISO 527-1, -2	20	MPa
Tensile Strain at Break (23 °C, 50 mm/min)	ISO 527-1, -2	32	%
Tensile Strain at Yield (23 °C, 50 mm/min)	ISO 527-1, -2	5	%
Flexural modulus (23 °C, 2 mm/min, Chord)	ISO 178	1300	MPa
<b>Impact</b>			
Notched izod impact strength (23 °C, Type 1, Notch A) <i>Note: Failure Mode: Complete</i>	ISO 180	11	kJ/m <sup>2</sup>
(- 40°C, Type 1, Notch A) <i>Note: Failure Mode: Complete</i>		5.3	
Multiaxial Impact Strength (23 °C, 2.2 m/s) <i>Note: Energy @ Max Load on 3.2 mm plq</i> Failure Mode: Ductile	ASTM D3763	18	J
(-40 °C, 2.2 m/s) <i>Note: Energy @ Max Load on 3.2 mm plq</i> Failure Mode: Ductile		28	J
<b>Hardness</b>			
Shore hardness D	ISO 868/ASTM D 2240	56	

Note: 15 seconds

---

**Thermal**

---

Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	85	°C
Heat deflection temperature A (1.80 MPa) Unannealed	ISO 75A-1, -2	50	°C
Vicat softening temperature (A50 (50°C/h 10N))	ISO 306	131	°C
Melting temperature	DSC	161	°C

Note: ISO 11357-3

---

**Additional Information**

---

Mold shrinkage ISO 294-4

Note: Please contact Equistar for shrinkage recommendations

---

---

**Additional Properties**

---

AUTOMOTIVE SPECIFICATIONS:  
Chrysler MS-DC256A CPN 4131

**Notes**

Typical properties; not to be construed as specifications.