



Hifax CA 1110 G4 LS C12477

Compounded Polyolefin

Product Description

Hifax CA 1110 G4 LS C12477 is a 10% talc filled PP copolymer, with good impact/stiffness balance and good UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in C12477 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

Status	Commercial	
Availability	Europe	(1)
Processing Method	Injection molding	
Features	Impact/stiffness balance, shrinkage and UV resistance.	
Typical Customer Applications	Used for moulding large complex parts, that require high impact strength as well good stiffness.	

Typical Properties

	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	17	g/10 min
Density (23 °C)	ISO 1183-1/A	0.98	g/cm ³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	16	MPa
Tens. Strain at Break	ISO 527-1, -2	400	%
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1150	MPa
Impact			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	40	kJ/m ²
Charpy Impact Strength, notched (-30 °C)	ISO 179-1/1eA	4	kJ/m ²
Charpy Impact Strength, unnotched (23 °C)	ISO 179-1/1eU	N.B.	kJ/m ²
Thermal			
Vicat Softening Temperature A (10 N)	ISO 306	117	°C
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	80	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affect the quality of this product
- Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.