



Hifax TRC 779XHS

Compounded Polyolefin

Product Description

Hifax TRC 779XHS high melt flow, medium high flexural modulus, paintable, mineral-filled thermoplastic elastomeric olefin (TEO) resin has an excellent balance of properties and processability. It was designed for use in multiple automotive exterior applications.

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	North America
Processing Methods	Injection Molding
Typical Customer Applications	Exterior Applications

Typical Properties	Method	Value	Unit
Physical			
Density (Method A)	ISO 1183	0.98	g/cm ³
Melt flow rate (MFR) (230 °C/ 2.16 kg)	ISO 1133	25	g/10 min
Mechanical			
Flexural modulus (23 °C)	ISO 178	1500	MPa
Tensile stress at yield	ISO 527	17	MPa

Additional Information

Mold shrinkage	ISO 294-4
----------------	-----------

Note: Please contact LyondellBasell for shrinkage recommendations.

Notes

Typical properties; not to be construed as specifications.