



Hifax TYC735P

Compounded Polyolefin

Product Description

Hifax TYC735P high melt flow, 1,150 MPa flexural modulus, UV-stabilized, paintable, mineral-filled thermoplastic elastomeric olefin (TEO) has an excellent combination of properties and processability. It was designed for use in multiple molded-in color and selectively decorated automotive exterior applications.

A non-UV-stabilized version, TYC735X, is also available for fully painted applications.

Product Characteristics

Status	Commercial: Active
Test Method used	ISO
Availability	North America
Processing Methods	Injection Molding
Features	Good Adhesion, Good Dimensional Stability, Durable, High Flow, Good Impact Resistance, Paintable, Good Stiffness, Good Weather Resistance
Typical Customer Applications	Bumpers, Exterior Applications

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	0.98	g/cm ³
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	25	g/10 min
<i>Note: Alternative test method is ASTM D 1238-01.</i>			
Mechanical			
Tensile Stress at Yield	ISO 527-1, -2	17.5	MPa
Tensile Strain at Yield	ISO 527-1, -2	14	%
Flexural modulus	ISO 178	1150	MPa
Impact			
Notched izod impact strength (23 °C)	ISO 180	46	kJ/m ²
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	86	°C
Heat deflection temperature A (1.80 MPa) Unannealed	ISO 75A-1, -2	53	°C
CLTE, Flow	ISO 11359-1, -2	4.5 x 10 ⁻⁵	cm/cm/°C
<i>Note: Determined over a temperature range of -30°C to 100°C. Alternative test method is ASTM E 228-95.</i>			
Additional Information			
Mold shrinkage	ISO 294-4		
<i>Note: Please contact Basell for shrinkage recommendations.</i>			

Notes

Typical properties; not to be construed as specifications.