



Hostacom EKC 330N E1 D7V721

Compounded Polyolefin

Product Description

Hostacom EKC 330N E1 D7V721 is a 16% talc filled PP copolymer, with good flowability, excellent impact/stiffness balance, good scratch resistance and outstanding blooming resistance at elevated temperatures. The product is also available as a customized color matched, pellet form. This grade is delivered in D7V721 color version.

This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

Product Characteristics

Status	Commercial	
Availability	Europe	(1)
Processing Method	Injection molding	
Features	Impact/stiffness balance, scratch resistance.	
Typical Customer Applications	Used for automotive interior trims.	

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	18	g/10 min
Density (23 °C)	ISO 1183-1/A	1.02	g/cm ³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	21	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1800	MPa
Impact			
Charpy Impact Strength, unnotched (23 °C)	ISO 179-1/1eU	NB	kJ/m ²
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	45	kJ/m ²
Charpy Impact Strength, notched (-30 °C)	ISO 179-1/1eA	5	kJ/m ²
Thermal			
Vicat Softening Temperature A (10 N)	ISO 306	132	°C
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	56	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affect the quality of this product
- Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.