



Hostacom EKC 485N

Compounded Polyolefin

Product Description

Hostacom EKC 485N is a 16% talc filled PP copolymer, with high stiffness, high impact resistance and very good scratch resistance. This grade is delivered in customer customized colors, this Data Sheet is giving general properties, some of them may be slightly altered upon color selected.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Product Characteristics

| | | |
|--------------------------------------|-------------------------------------|-----|
| Status | Commercial | |
| Availability | Europe | (1) |
| Processing Method | Injection molding | |
| Features | Stiffness, impact resistance. | |
| Typical Customer Applications | Used for automotive interior trims. | |

| Typical Properties | Method | Value | Unit |
|--|--------------|-------|-------------------|
| Physical | | | |
| Melt Flow Rate (230 °C, 2.16 kg) | ISO 1133 | 13 | g/10 min |
| Density (23 °C) | ISO 1183-1/A | 1.02 | g/cm ³ |
| Mechanical | | | |
| Flexural Modulus (23 °C) Tech. A | ISO 178/A1 | 1900 | MPa |
| Impact | | | |
| Izod Impact strength, notched (23 °C) | ISO 180/1A | 25 | kJ/m ² |
| Izod Impact strength, notched (-40 °C) | ISO 180/1A | 3 | kJ/m ² |
| Thermal | | | |
| Heat Deflection Temperature B (0.45 MPa) | ISO 75-1, -2 | 100 | °C |

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.