



## Hifax ERC 347P G14008

### Compounded Polyolefin

#### Product Description

Hifax ERC 347P G14008 is a 30% talc filled PP copolymer, with excellent impact/stiffness balance and good flowability. Product is available as a customized color matched, pellet form. This grade is delivered in G14008 color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

#### Product Characteristics

<b>Status</b>	Commercial	
<b>Availability</b>	Europe	(1)
<b>Processing Method</b>	Injection molding	
<b>Features</b>	Flowability, impact/stiffness balance.	
<b>Typical Customer Applications</b>	Used for automotive interior trims; its formula is improved to offer better aspect especially on tiger stripes.	

#### Typical Properties

	Method	Value	Unit
<b>Physical</b>			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	24	g/10 min
Density (23 °C)	ISO 1183-1/A	1.14	g/cm <sup>3</sup>
<b>Mechanical</b>			
Flexural Strength (23 °C) Tech. A	ISO 178/A1	2500	MPa
<b>Impact</b>			
Izod Impact Strength, notched (-30 °C)	ISO 180/1A	2.5	kJ/m <sup>2</sup>

#### Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

#### Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.