



## Hostacom HKG 339N C12616

### Compounded Polyolefin

#### Product Description

Hostacom HKG 339N C12616 is a mixed filler grade, elastomer modified PP, with a 20% of glass fiber reinforcing and a 20% of talc filling, with good processability, excellent impact/stiffness balance and good dimensional stability. Please contact Basell for shrinkage recommendations. The product is available as a customized color matched, pellet form. This grade is delivered in C12616 color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

#### Product Characteristics

<b>Status</b>	Commercial	
<b>Availability</b>	Europe	(1)
<b>Processing Method</b>	Injection molding	
<b>Features</b>	Processability, impact/stiffness balance, dimensional stability.	

**Typical Customer Applications** Used for good balance of stiffness and impact performance, that require good balance of stiffness and impact performance, as well as superior dimensional stability.

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	11	g/10 min
Density (23 °C)	ISO 1183-1/A	1.22	g/cm <sup>3</sup>
<b>Mechanical</b>			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	55	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	6200	MPa
<b>Impact</b>			
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	8	kJ/m <sup>2</sup>
Charpy Impact Strength, notched (-30 °C)	ISO 179-1/1eA	6	kJ/m <sup>2</sup>
<b>Thermal</b>			
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	130	°C

#### Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

#### Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.