



## Hostacom PF062-3C

### Compounded Polyolefin

#### Product Description

Hostacom PF062-3C high melt flow, 5,200 MPa flexural modulus, precolored, chemically coupled, 30% glass fiber-reinforced polypropylene homopolymer has good impact strength, high stiffness and very good moldfilling capability.

#### Product Characteristics

<b>Status</b>	Commercial: Restricted
<b>Test Method used</b>	ASTM
<b>Availability</b>	North America
<b>Processing Methods</b>	Injection Molding
<b>Features</b>	Chemically Coupled, High Flow , Homopolymer, Good Impact Resistance , Good Moldability , Good Processability, Good Stiffness , Good Thermal Stability, Warp Resistant

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Density -Specific Gravity	ASTM D 792	1.12	sp gr 23/23°C
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	20	g/10 min
<b>Mechanical</b>			
Flexural Modulus	ASTM D 790	5200	MPa
Tensile Strength @ Yield	ASTM D 638	90	MPa
<b>Impact</b>			
Notched Izod Impact (23 °C)	ASTM D 256	85	J/m

#### Notes

Typical properties: not to be construed as specifications.