



Hostacom TRC 352N G22749

Compounded Polyolefin

IMDS Number: 19524190

Product Description

Hostacom TRC 352N G22749 is a 20% talc filled PP copolymer, with good flowability, excellent impact/stiffness balance, good scratch resistance and outstanding blooming resistance at elevated temperatures. Product is available as a customized color matched, pellet form. This grade is delivered in G22749 color version.

This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

Product Characteristics

| | | |
|--------------------------------------|---|-----|
| Status | Commercial | |
| Availability | Europe | (1) |
| Processing Method | Injection molding | |
| Features | Impact/stiffness balance, scratch resistance. | |
| Typical Customer Applications | Developed for indoor/interior applications. | |

| Typical Properties | Method | Value | Unit |
|---|---------------|-------|-------------------|
| Physical | | | |
| Melt Flow Rate (230 °C, 2.16 kg) | ISO 1133 | 18 | g/10 min |
| Density (23 °C) | ISO 1183-1/A | 1.04 | g/cm ³ |
| Mechanical | | | |
| Tensile Stress at Yield (23 °C) | ISO 527-1, -2 | 22 | MPa |
| Flexural Modulus (23 °C) Tech. A | ISO 178/A1 | 2000 | MPa |
| Impact | | | |
| Charpy Impact Strength, notched (23 °C) | ISO 179-1/1eA | 30 | kJ/m ² |
| Charpy Impact Strength, notched (-30 °C) | ISO 179-1/1eA | 3 | kJ/m ² |
| Charpy Impact Strength, unnotched (23 °C) | ISO 179-1/1eU | NB | kJ/m ² |
| Thermal | | | |
| Vicat Softening Temperature A (10 N) | ISO 306 | 136 | °C |
| Heat Deflection Temperature A (1.8 MPa) | ISO 75-1, -2 | 54 | °C |

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.