



## Hostacom X M3 T14 C12507

### Compounded Polyolefin

#### Product Description

Hostacom X M3 T14 C12507 is a 30% talc filled PP copolymer, with medium flowability, good UV resistance, low odour, low fogging and low emissions. The product is available in different color matched, pellet form. This grade is delivered in C12507 color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

#### Product Characteristics

<b>Status</b>	Commercial	
<b>Availability</b>	Europe	(1)
<b>Processing Method</b>	Injection molding	
<b>Features</b>	UV resistance.	
<b>Typical Customer Applications</b>	Used for automotive interior trims.	

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	7	g/10 min
Density (23 °C)	ISO 1183-1/A	1.14	g/cm <sup>3</sup>
<b>Mechanical</b>			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	24	MPa
Tens. Strain at Break	ISO 527-1, -2	5	%
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	2600	MPa
<b>Impact</b>			
Charpy Impact Strength, unnotched (23 °C)	ISO 179-1/1eU	40	kJ/m <sup>2</sup>
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	8	kJ/m <sup>2</sup>
<b>Thermal</b>			
Vicat Softening Temperature A (10 N)	ISO 306	70	°C
Heat Deflection Temperature A (1.8 MPa)	ISO 75-1, -2	65	°C

#### Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affect the quality of this product
- Keep material completely dry for good processing.

#### Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.