



Hostacom XBR 169 G G23088

Compounded Polyolefin

IMDS Number: 95688135

Product Description

Hostacom XBR 169 G G23088 is a 15% talc filled PP copolymer, with good processability, excellent impact/stiffness balance, good surface appearance and good scratch resistance. Product is available as a customized color matched, pellet form. It has been designed using the latest advancements in resin synthesis and compounding technology. This grade is delivered in G23088 color version.

This grade is not intended for medical, pharmaceutical, food, drinking water and all applications not listed in the supported list. For more information please contact our sales representatives.

Product Characteristics

Status	Leaving the market	
Availability	Europe	(1)
Processing Method	Injection molding	
Features	Excellent impact/stiffness balance, good scratch resistance, good surface appearance.	
Typical Customer Applications	Designed for automotive instrument panel; reduction of mineral filler contributes to reduction of final part weight.	

Typical Properties

	Method	Value	Unit
Physical			
Melt Flow Rate (230 °C, 2.16 kg)	ISO 1133	15	g/10 min
Density (23 °C)	ISO 1183-1/A	1.02	g/cm ³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	17	MPa
Flexural Modulus (23 °C) Tech. A	ISO 178/A1	1650	MPa
Impact			
Charpy Impact Strength, notched (-40 °C)	ISO 179-1/1eA	2.5	kJ/m ²
Izod Impact strength, notched (23 °C)	ISO 180/1A	30	kJ/m ²
Izod Impact strength, notched (-40 °C)	ISO 180/1A	3.5	kJ/m ²
Charpy Impact Strength, notched (23 °C)	ISO 179-1/1eA	35	kJ/m ²
Thermal			
Heat Deflection Temperature B (0.45 MPa)	ISO 75-1, -2	100	°C

Product Storage and Handling

- Product should be stored in dry conditions at temperatures below 50°C and protected from UV-light.
- Improper storage may bring damage to the packaging and can negatively affects on the quality of this product
- Keep material completely dry for good processing.

Notes

Typical properties; not to be construed as specifications.

(1) : Here is indicated the region where the material is produced. For importation or demand of a local equivalent grade, please contact our Sales Representatives.