

**Technical Data Sheet**

***Polyfort* TPO-15T BK2030BLK**



Polyolefin, Unspecified

**Product Description**

15% Mineral Filled Thermoplastic Polyolefin Melt Flow Adjustable for Application Colors Available Add "U" for UV Stabilized Add "H" for Heat Stabilized

**Filler/Reinforcement**      Mineral, 15%

<b>Typical Properties</b>	<b>Nominal Value</b>	<b>Units</b>	<b>Test Method</b>
<b>Physical</b>			
Melt Flow Rate	18	g/10 min	ASTM D1238
Density - Specific Gravity	1.04	g/cm <sup>3</sup>	ASTM D792
<b>Mechanical</b>			
Tensile Strength at Yield	20.7	MPa	ASTM D638
Flexural Modulus	1380	MPa	ASTM D790
<b>Impact</b>			
Notched Izod Impact	370	J/m	ASTM D256