



## Sequel 1980-PUV

### Compounded Polyolefin

#### Product Description

Sequel 1980-PUV high melt flow, high flexural modulus, UV-stabilized, mineral-filled, thermoplastic elastomeric olefin has an excellent balance of properties and processability.

#### Product Characteristics

<b>Status</b>	Commercial: Active
<b>Test Method used</b>	ISO
<b>Availability</b>	North America
<b>Processing Methods</b>	Injection Molding
<b>Features</b>	Good Flow , Good Moldability , Good Weather Resistance
<b>Typical Customer Applications</b>	Bumpers, Exterior Applications

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	25	g/10 min
Density (Method A)	ISO 1183	1.04	g/cm <sup>3</sup>
<b>Mechanical</b>			
Flexural modulus (23 °C)	ISO 178	1700	MPa
<b>Additional Information</b>			
Mold shrinkage	ISO 294-4		
<i>Note: Please contact LyondellBasell for shrinkage recommendations.</i>			

#### Notes

Typical properties; not to be construed as specifications.