



## Softell CA7469A

### Advanced Polyolefin

#### Product Description

Softell CA 7469 A is a reactor TPO (thermoplastic polyolefin) manufactured using the LyondellBasell's proprietary *Catalloy* process technology. It is used for the extrusion and calendering processes for applications such as TPO skins, W&C and technical compounds. It is also utilized as building block in TPE and TPV compounds. Softell CA 7469 A exhibits low stiffness, low gloss, low hardness and good impact resistance. The grade is available in natural pellet form. For regulatory compliance information please refer to Softell CA 7469 A Product Stewardship Bulletin (PSB)

#### Product Characteristics

<b>Status</b>	Commercial: Active
<b>Test Method used</b>	ISO
<b>Availability</b>	Europe, North America, Asia-Pacific, Australia/NZ, Africa-Middle East, Latin America
<b>Processing Methods</b>	Extrusion Compounding, Calendering
<b>Features</b>	Good Flexibility, Low Temperature Flexibility, Low Gloss, Low Hardness, Medium Heat Resistance, Low Temperature Impact Resistance
<b>Typical Customer Applications</b>	Automotive Parts, Building and Construction, Impact modification, Instrument Panels, Soft Profile & Sheets, TPO Foils and Skins, Wire & Cable

Typical Properties	Method	Value	Unit
<b>Physical</b>			
Density (Method A)	ISO 1183	0.88	g/cm <sup>3</sup>
Melt flow rate (MFR) (230°C/2.16Kg)	ISO 1133	0.5	g/10 min
<b>Mechanical</b>			
Tensile Stress at Break	ISO 527-1, -2	7	MPa
Tensile Strain at Break	ISO 527-1, -2	> 400	%
Flexural modulus	ISO 178	120	MPa
<b>Impact</b>			
Notched izod impact strength (- 40°C)	ISO 180	70	kJ/m <sup>2</sup>
<b>Hardness</b>			
Shore hardness (Shore A)	ISO 868	86	
<b>Thermal</b>			
Melting temperature	DSC	145	°C
<i>Note: ISO 11357-3</i>			
<b>Optical</b>			
Gloss (45°, 50 µm)	ASTM D 2457	4	%

#### Notes

Typical properties; not to be construed as specifications.