



**Product Data Sheet &
General Processing Conditions**

**RTP 683 FR
Acrylonitrile Butadiene Styrene
(ABS)
Carbon Fiber
Flame Retardant**

The RTP 680 FR Series offers a good combination of physical properties, stiffness, ignition resistance and the ability to be fabricated to close dimensional tolerances.

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	20 %	20 %	
Specific Gravity	1.30	1.30	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0010 - 0.0020 in/in	0.10 - 0.20 %	D 955
Water Absorption, 24 hrs @ 23°C	0.170 %	0.170 %	D 570
MECHANICAL			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.0 ft-lbs/in	53 J/m	D 256
unnotched 1/8 in (3.2 mm) section	5.0 ft-lbs/in	267 J/m	D 4812
Tensile Strength	17000 psi	117 MPa	D 638
Tensile Elongation	1.5 %	1.5 %	D 638
Tensile Modulus	2.00 x 10 ⁶ psi	13790 MPa	D 638
Flexural Strength	22000 psi	152 MPa	D 790
Flexural Modulus	1.80 x 10 ⁶ psi	12411 MPa	D 790
Hardness Rockwell, R	108	108	D 785
ELECTRICAL			
Volume Resistivity	< 1E5 ohm.cm	< 1E5 ohm.cm	D 257
THERMAL			
Deflection Temperature @ 264 psi (1820 kPa)	225 °F	107 °C	D 648
@ 66 psi (455 kPa)	230 °F	110 °C	D 648
Ignition Resistance* Flammability**	V-0 @ 1/16 in	V-0 @ 1.5 mm	D 3801

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	400 - 460 °F	204 - 238 °C
Mold Temperature	145 - 185 °F	63 - 85 °C
Drying	2 hrs @ 180 °F	2 hrs @ 82 °C
Moisture Content	0.10 %	0.10 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

Desiccant Type Dryer Required.