




**Product Data Sheet &  
General Processing Conditions**

**RTP 683 HB  
Acrylonitrile Butadiene Styrene  
(ABS)  
Carbon Fiber  
UL94 HB**



The RTP 680 HB are carbon fiber reinforced ABS. These materials offer a good combination of physical properties, stiffness and the ability to be fabricated to close dimensional tolerances.

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Primary Additive	20 %	20 %	
Specific Gravity	1.13	1.13	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0005 - 0.0015 in/in	0.05 - 0.15 %	D 955
Water Absorption, 24 hrs @ 23°C	0.170 %	0.170 %	D 570

**MECHANICAL**

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.1 ft-lbs/in	59 J/m	D 256
unnotched 1/8 in (3.2 mm) section	6.0 ft-lbs/in	320 J/m	D 4812
Tensile Strength	16000 psi	110 MPa	D 638
Tensile Elongation	1.5 %	1.5 %	D 638
Tensile Modulus	2.00 x 10 <sup>6</sup> psi	13790 MPa	D 638
Flexural Strength	23000 psi	159 MPa	D 790
Flexural Modulus	1.65 x 10 <sup>6</sup> psi	11377 MPa	D 790
Hardness Rockwell, R	108	108	D 785

**ELECTRICAL**

Volume Resistivity	< 9.9E1 ohm.cm	< 9.9E1 ohm.cm	D 257
--------------------	----------------	----------------	-------

**THERMAL**

Deflection Temperature @ 264 psi (1820 kPa)	225 °F	107 °C	D 648
@ 66 psi (455 kPa)	230 °F	110 °C	D 648
Ignition Resistance* Flammability	HB @ 1/16 in	HB @ 1.5 mm	UL94

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	400 - 460 °F	204 - 238 °C
Mold Temperature	145 - 185 °F	63 - 85 °C
Drying	2 hrs @ 180 °F	2 hrs @ 82 °C
Moisture Content	0.10 %	0.10 %
Dew Point	0 °F	-18 °C

**PROCESSING NOTES**

---

Desiccant Type Dryer Required.