



**Product Data Sheet &
General Processing Conditions**

**ESD C 703
High Density Polyethylene (HDPE)
Glass Fiber
ESD Protection
Electrically Conductive**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.18	1.18	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0040 - 0.0080 in/in	0.40 - 0.80 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.0 ft-lbs/in	53 J/m	D 256
unnotched 1/8 in (3.2 mm) section	4.0 ft-lbs/in	214 J/m	D 4812
Tensile Strength	5000 psi	34 MPa	D 638
Tensile Elongation	3.0 - 6.0 %	3.0 - 6.0 %	D 638
Tensile Modulus	0.75 x 10 ⁶ psi	5171 MPa	D 638
Flexural Strength	7000 psi	48 MPa	D 790
Flexural Modulus	0.45 x 10 ⁶ psi	3103 MPa	D 790

ELECTRICAL

Volume Resistivity	< 1E3 ohm.cm	< 1E3 ohm.cm	D 257
Surface Resistivity	< 1E6 ohm/sq	< 1E6 ohm/sq	D 257
Surface Resistance	< 1E5 ohm	< 1E5 ohm	ESD STM11.11
Static Decay MIL-PRF-81705D, 5kV to 50 V, 12% RH	< 2.00 s	< 2.00 s	FTMS101C 4046.1

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	380 - 450 °F	193 - 232 °C
Mold Temperature	70 - 150 °F	21 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C