




**Product Data Sheet &
General Processing Conditions**

**RTP 3405-4
Liquid Crystal Polymer (LCP)
Glass Fiber
UL94 V-0**



The RTP 3400 series of compounds is based on a self-reinforcing crystalline polymer. Liquid crystal polymers offer outstanding heat and chemical resistance. These unique properties combined with excellent processability lend these compounds to a diverse range of applications.

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	30 %	30 %	
Specific Gravity	1.61	1.61	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0002 - 0.0010 in/in	0.02 - 0.10 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.8 ft-lbs/in	96 J/m	D 256
notched 1/8 in (3.2 mm) section	10.0 ft-lbs/in	534 J/m	D 4812
Tensile Strength	17000 psi	117 MPa	D 638
Tensile Elongation	1.0 - 2.0 %	1.0 - 2.0 %	D 638
Tensile Modulus	2.30 x 10 ⁶ psi	15858 MPa	D 638
Flexural Strength	24000 psi	165 MPa	D 790
Flexural Modulus	2.10 x 10 ⁶ psi	14480 MPa	D 790
Hardness Rockwell, R	105	105	D 785

ELECTRICAL

Dielectric Strength, S/T, in oil	650 VPM	25.6 kV/mm	D 149
Dielectric Constant, 1 MHz, Dry	3.1	3.1	D 150
Dissipation Factor, 1 MHz, Dry	0.0300	0.0300	D 150

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	580 °F	304 °C	D 648
Ignition Resistance*			
Flammability	V-0 @ 0.012 in	V-0 @ 0.3 mm	UL94
Flammability	V-0 @ 1/16 in	V-0 @ 1.5 mm	UL94

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 18000 psi	69 - 124 MPa
Melt Temperature	685 - 750 °F	363 - 399 °C
Mold Temperature	150 - 200 °F	66 - 93 °C
Drying	8 hrs @ 300 °F	8 hrs @ 149 °C
Dew Point	-20 °F	-29 °C