



**Product Data Sheet &
General Processing Conditions**

**ESD A 700 A
Low Density Polyethylene (LDPE)
ESD Protection
Static Dissipative**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.00	1.00	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0180 - 0.0250 in/in	1.80 - 2.50 %	D 955
MECHANICAL			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	No Break	No Break	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	1200 psi	8 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.05 x 10 ⁶ psi	345 MPa	D 638
Flexural Strength	1400 psi	10 MPa	D 790
Flexural Modulus	0.05 x 10 ⁶ psi	345 MPa	D 790

ELECTRICAL

Volume Resistivity	1000 - 9.9E+09 ohm.cm	1000 - 9.9E+09 ohm.cm	D 257
Surface Resistivity	1.0E+5 - 9.9E+11 ohm/sq	1.0E+5 - 9.9E+11 ohm/sq	D 257
Surface Resistance	1.0E+4 - 9.9E+10 ohm	1.0E+4 - 9.9E+10 ohm	ESD STM11.11
Static Decay MIL-PRF-81705D, 5kV to 50 V, 12% RH	< 2.00 s	< 2.00 s	FTMS101C 4046.1

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	380 - 450 °F	193 - 232 °C
Mold Temperature	70 - 150 °F	21 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C