



**Product Data Sheet &
General Processing Conditions**

**ESD C 700 A
Low Density Polyethylene (LDPE)
ESD Protection
Electrically Conductive**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.04	1.04	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0170 - 0.0220 in/in	1.70 - 2.20 %	D 955
MECHANICAL			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	8.0 ft-lbs/in	427 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	1500 psi	10 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.05 x 10 ⁶ psi	345 MPa	D 638
Flexural Strength	2000 psi	14 MPa	D 790
Flexural Modulus	0.05 x 10 ⁶ psi	345 MPa	D 790
ELECTRICAL			
Volume Resistivity	< 1E3 ohm.cm	< 1E3 ohm.cm	D 257
Surface Resistivity	< 1E6 ohm/sq	< 1E6 ohm/sq	D 257
Surface Resistance	< 1E5 ohm	< 1E5 ohm	ESD STM11.11
Static Decay MIL-PRF-81705D, 5kV to 50 V, 12% RH	< 2.00 s	< 2.00 s	FTMS101C 4046.1

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	380 - 450 °F	193 - 232 °C
Mold Temperature	70 - 150 °F	21 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C