



**Product Data Sheet &  
General Processing Conditions**

**RTP 700 A FR UV  
Low Density Polyethylene (LDPE)  
Flame Retardant  
UV Stabilized**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Specific Gravity	1.22	1.22	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0250 - 0.0300 in/in	2.50 - 3.00 %	D 955
<b>MECHANICAL</b>			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	8.0 ft-lbs/in	427 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	1200 psi	8 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.05 x 10 <sup>6</sup> psi	345 MPa	D 638
Flexural Strength	1300 psi	9 MPa	D 790
Flexural Modulus	0.04 x 10 <sup>6</sup> psi	276 MPa	D 790
<b>ELECTRICAL</b>			
Volume Resistivity	> 1E16 ohm.cm	> 1E16 ohm.cm	D 257
<b>THERMAL</b>			
Ignition Resistance* Flammability**	V-0 @ 1/16 in	V-0 @ 1.5 mm	D 3801

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

\*\* Values per RTP Company testing.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	380 - 450 °F	193 - 232 °C
Mold Temperature	70 - 150 °F	21 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C