



**Product Data Sheet &
General Processing Conditions**

**RTP 203 C
Nylon 11 (PA)
Glass Fiber
79% Renewable Resource Content***

*Based on % of total compound weight.

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	20 %	20 %	
Specific Gravity	1.18	1.18	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0020 - 0.0040 in/in	0.20 - 0.40 %	D 955
MECHANICAL			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	2.0 ft-lbs/in	107 J/m	D 256
unnotched 1/8 in (3.2 mm) section	11.5 ft-lbs/in	614 J/m	D 4812
Tensile Strength	12000 psi	83 MPa	D 638
Tensile Elongation	3.0 - 4.0 %	3.0 - 4.0 %	D 638
Tensile Modulus	0.70 x 10 ⁶ psi	4826 MPa	D 638
Flexural Strength	17000 psi	117 MPa	D 790
Flexural Modulus	0.70 x 10 ⁶ psi	4826 MPa	D 790
THERMAL			
Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	435 - 550 °F	224 - 288 °C
Mold Temperature	100 - 150 °F	38 - 66 °C
Drying	4 hrs @ 175 °F	4 hrs @ 79 °C
Moisture Content	0.20 %	0.20 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

Desiccant Type Dryer Required.