



**Product Data Sheet &  
General Processing Conditions**

**RTP 204 G FR HS  
Nylon 4/6 (PA)  
Glass Fiber  
Flame Retardant  
Heat Stabilized  
Dry As Molded**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Primary Additive	25 %	25 %	
Specific Gravity	1.65	1.65	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0030 - 0.0050 in/in	0.30 - 0.50 %	D 955
Water Absorption, 24 hrs @ 23°C	1.800 %	1.800 %	D 570

**MECHANICAL**

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.1 ft-lbs/in	59 J/m	D 256
unnotched 1/8 in (3.2 mm) section	11.0 ft-lbs/in	587 J/m	D 4812
Tensile Strength	20000 psi	138 MPa	D 638
Tensile Elongation	2.0 - 3.0 %	2.0 - 3.0 %	D 638
Tensile Modulus	1.35 x 10 <sup>6</sup> psi	9308 MPa	D 638
Flexural Strength	31000 psi	214 MPa	D 790
Flexural Modulus	1.35 x 10 <sup>6</sup> psi	9308 MPa	D 790
Hardness Rockwell, R	120	120	D 785

**ELECTRICAL**

Volume Resistivity	> 1E14 ohm.cm	> 1E14 ohm.cm	D 257
--------------------	---------------	---------------	-------

**THERMAL**

Deflection Temperature @ 264 psi (1820 kPa)	540 °F	282 °C	D 648
Ignition Resistance* Flammability**	V-0 @ 1/32 in	V-0 @ 0.8 mm	D 3801
Limiting Oxygen Index**	37.0 %	37.00 %	D 2863

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

\*\* Values per RTP Company testing.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	560 - 620 °F	293 - 327 °C
Mold Temperature	175 - 300 °F	79 - 149 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C
Moisture Content	0.05 %	0.05 %
Dew Point	-40 °F	-40 °C