



**Product Data Sheet &
General Processing Conditions**

**RTP 299 A X 108950 B
Nylon 6 (PA)
High Gravity Compound**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	3.00	3.00	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0050 - 0.0100 in/in	0.50 - 1.00 %	D 955
MECHANICAL			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	0.6 ft-lbs/in	32 J/m	D 256
unnotched 1/8 in (3.2 mm) section	5.0 ft-lbs/in	267 J/m	D 4812
Tensile Strength	4000 psi	28 MPa	D 638
Tensile Elongation	1.0 - 2.0 %	1.0 - 2.0 %	D 638
Tensile Modulus	0.70 x 10 ⁶ psi	4826 MPa	D 638
Flexural Strength	8000 psi	55 MPa	D 790
Flexural Modulus	0.80 x 10 ⁶ psi	5516 MPa	D 790

THERMAL

Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635
--	--------------	-------------	-------

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	470 - 535 °F	243 - 279 °C
Mold Temperature	130 - 200 °F	54 - 93 °C
Drying	2 hrs @ 180 °F	2 hrs @ 82 °C
Moisture Content	0.20 %	0.20 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

Desiccant Type Dryer Required.