



**Product Data Sheet &  
General Processing Conditions**

**RTP 200 AR 15  
Nylon 6/6 (PA)  
Aramid Fiber**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Primary Additive	15 %	15 %	
Specific Gravity	1.17	1.17	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0100 - 0.0200 in/in	1.00 - 2.00 %	D 955

**MECHANICAL**

Impact Strength, Izod notched 1/8 in (3.2 mm) section	0.8 ft-lbs/in	43 J/m	D 256
unnotched 1/8 in (3.2 mm) section	10.5 ft-lbs/in	561 J/m	D 4812
Tensile Strength	13000 psi	90 MPa	D 638
Tensile Elongation	6.0 - 8.0 %	6.0 - 8.0 %	D 638
Tensile Modulus	0.60 x 10 <sup>6</sup> psi	4137 MPa	D 638
Flexural Strength	20000 psi	138 MPa	D 790
Flexural Modulus	0.60 x 10 <sup>6</sup> psi	4137 MPa	D 790

**ELECTRICAL**

Volume Resistivity	1E14 - 1E16 ohm.cm	1E14 - 1E16 ohm.cm	D 257
--------------------	--------------------	--------------------	-------

**THERMAL**

Deflection Temperature @ 264 psi (1820 kPa)	300 °F	149 °C	D 648
Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

\*\* Values per RTP Company testing.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 18000 psi	69 - 124 MPa
Melt Temperature	530 - 570 °F	277 - 299 °C
Mold Temperature	150 - 225 °F	66 - 107 °C
Drying	4 hrs @ 175 °F	4 hrs @ 79 °C
Moisture Content	0.20 %	0.20 %
Dew Point	0 °F	-18 °C

**PROCESSING NOTES**

Desiccant Type Dryer Required.