



**Product Data Sheet &
General Processing Conditions**

**RTP 200 TC-C-55
Nylon 6/6 (PA)
Thermally Conductive
Electrically Conductive**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.59	1.59	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0015 - 0.0040 in/in	0.15 - 0.40 %	D 955
MECHANICAL			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	0.5 ft-lbs/in	27 J/m	D 256
unnotched 1/8 in (3.2 mm) section	1.5 ft-lbs/in	80 J/m	D 4812
Tensile Strength	7000 psi	48 MPa	D 638
Tensile Elongation	< 1.0 %	< 1.0 %	D 638
Tensile Modulus	2.65 x 10 ⁶ psi	18272 MPa	D 638
Flexural Strength	12000 psi	83 MPa	D 790
Flexural Modulus	2.35 x 10 ⁶ psi	16203 MPa	D 790
ELECTRICAL			
Volume Resistivity	< 1E2 ohm.cm	< 1E2 ohm.cm	D 257
Surface Resistivity	< 1E4 ohm/sq	< 1E4 ohm/sq	D 257
THERMAL			
Thermal Conductivity Through-plane	31.73 (BTU.in)/(hr.ft ² .°F)	4.57 W/(m.K)	E 1530
In-plane	178.47 (BTU.in)/(hr.ft ² .°F)	25.72 W/(m.K)	E 1461-92

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 18000 psi	69 - 124 MPa
Melt Temperature	530 - 570 °F	277 - 299 °C
Mold Temperature	200 - 275 °F	93 - 135 °C
Drying	4 hrs @ 175 °F	4 hrs @ 79 °C
Moisture Content	0.20 %	0.20 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

Desiccant Type Dryer Required.