



**Product Data Sheet &
General Processing Conditions**

**RTP 203 FR
Nylon 6/6 (PA)
Glass Fiber
Flame Retardant
UL94 V-0**



The RTP series of flame retardant, glass fiber reinforced nylon materials are designed to provide the optimal balance of strength, electrical and ignition resistance properties while exhibiting excellent processing characteristics. RTP 203 FR possesses UL94 V-0 certification, as well as a complete range of UL94 electrical ratings and RTI assignment required for many EEE applications.

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	20 %	20 %	
Specific Gravity	1.58	1.58	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0020 - 0.0035 in/in	0.20 - 0.35 %	D 955
Water Absorption, 24 hrs @ 23°C	0.700 %	0.700 %	D 570

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.4 ft-lbs/in	75 J/m	D 256
unnotched 1/8 in (3.2 mm) section	12.0 ft-lbs/in	641 J/m	D 4812
Tensile Strength	18500 psi	128 MPa	D 638
Tensile Elongation	2.0 - 3.0 %	2.0 - 3.0 %	D 638
Tensile Modulus	1.20 x 10 ⁶ psi	8274 MPa	D 638
Flexural Strength	30000 psi	207 MPa	D 790
Flexural Modulus	1.10 x 10 ⁶ psi	7584 MPa	D 790
Hardness Rockwell, R	116	116	D 785

ELECTRICAL

Dielectric Strength, S/T, in oil	475 VPM	18.7 kV/mm	D 149
Dielectric Constant, 1 MHz, Dry	3.8	3.8	D 150
Dissipation Factor, 1 MHz, Dry	0.0150	0.0150	D 150
Volume Resistivity	> 1E14 ohm.cm	> 1E14 ohm.cm	D 257

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	440 °F	227 °C	D 648
@ 66 psi (455 kPa)	475 °F	246 °C	D 648
Ignition Resistance* Flammability	V-0 @ 1/32 in	V-0 @ 0.8 mm	UL94
Limiting Oxygen Index	34.0 %	34.00 %	D 2863

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 18000 psi	69 - 124 MPa

Melt Temperature	530 - 570 °F	277 - 299 °C
Mold Temperature	150 - 225 °F	66 - 107 °C
Drying	4 hrs @ 175 °F	4 hrs @ 79 °C
Moisture Content	0.20 %	0.20 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

Desiccant Type Dryer Required.