



**Product Data Sheet &
General Processing Conditions**

**RTP 205.3 RC HS
Nylon 6/6 (PA)
Glass Fiber
Heat Stabilized**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE **STANDARD**

Primary Additive	33 %	
Density	1.39 g/cm ³	ISO 1183
Shrinkage, 4 mm Thickness		
Flow direction	0.10 - 0.40 %	ASTM D 955

MECHANICAL

Impact Strength, Izod		
Notched, 4 mm thickness	11 kJ/m ²	ISO 180/1A
Tensile Strength	207 MPa	ISO 527
Tensile Elongation	3.5 %	ISO 527
Tensile Modulus	11300 MPa	ISO 527
Flexural Strength	280 MPa	ISO 178
Flexural Modulus	10000 MPa	ISO 178

THERMAL

Heat Deflection Temperature		
@ 1.80 MPa	250 °C	ISO 75
Ignition Resistance*		
Flammability**	HB @ 1.5 mm	ISO 1210

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
 Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.
 * This rating is not intended to reflect hazards of this or any other material under actual fire conditions.
 ** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

Injection Pressure	70 - 125 MPa
Injection Pressure	680 - 1240 bar
Melt Temperature	275 - 300 °C
Mold Temperature	65 - 105 °C
Drying	4 hrs @ 80 °C
Moisture Content	0.20 %
Dew Point	-25 °C

PROCESSING NOTES

Desiccant Type Dryer Required.