



**Product Data Sheet &  
General Processing Conditions**

**RTP 283 H  
Impact-Modified Nylon 6/6 (PA)  
Carbon Fiber**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Primary Additive	20 %	20 %	
Specific Gravity	1.17	1.17	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0010 - 0.0030 in/in	0.10 - 0.30 %	D 955

**MECHANICAL**

Impact Strength, Izod notched 1/8 in (3.2 mm) section	3.0 ft-lbs/in	160 J/m	D 256
unnotched 1/8 in (3.2 mm) section	17.0 ft-lbs/in	908 J/m	D 4812
Tensile Strength	21000 psi	145 MPa	D 638
Tensile Elongation	3.0 - 4.0 %	3.0 - 4.0 %	D 638
Tensile Modulus	1.60 x 10 <sup>6</sup> psi	11032 MPa	D 638
Flexural Strength	33000 psi	228 MPa	D 790
Flexural Modulus	1.40 x 10 <sup>6</sup> psi	9653 MPa	D 790

**ELECTRICAL**

Volume Resistivity	1E1 - 1E3 ohm.cm	1E1 - 1E3 ohm.cm	D 257
Surface Resistivity	1E4 - 1E6 ohm/sq	1E4 - 1E6 ohm/sq	D 257

**THERMAL**

Deflection Temperature @ 264 psi (1820 kPa)	450 °F	232 °C	D 648
Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

\*\* Values per RTP Company testing.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 18000 psi	69 - 124 MPa
Melt Temperature	530 - 570 °F	277 - 299 °C
Mold Temperature	150 - 225 °F	66 - 107 °C
Drying	4 hrs @ 175 °F	4 hrs @ 79 °C
Moisture Content	0.20 %	0.20 %
Dew Point	0 °F	-18 °C

**PROCESSING NOTES**

Desiccant Type Dryer Required.