



**Product Data Sheet &
General Processing Conditions**

**RTP 299 X 137077
Nylon 6/6 (PA)
Thermally Conductive
Electrically Conductive**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
-------------------	----------------	------------------	------------------

Specific Gravity	1.63	1.63	D 792
------------------	------	------	-------

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	0.5 ft-lbs/in	27 J/m	D 256
unnotched 1/8 in (3.2 mm) section	2.0 ft-lbs/in	107 J/m	D 4812
Tensile Strength	9000 psi	62 MPa	D 638
Tensile Elongation	< 1.0 %	< 1.0 %	D 638
Tensile Modulus	1.90 x 10 ⁶ psi	13100 MPa	D 638
Flexural Strength	13500 psi	93 MPa	D 790
Flexural Modulus	1.80 x 10 ⁶ psi	12411 MPa	D 790

ELECTRICAL

Volume Resistivity	< 1E2 ohm.cm	< 1E2 ohm.cm	D 257
Surface Resistivity	< 1E4 ohm/sq	< 1E4 ohm/sq	D 257

THERMAL

Thermal Conductivity			
Through-plane	31.25 (BTU.in)/(hr.ft ² .°F)	4.50 W/(m.K)	E 1530
In-plane	125.00 (BTU.in)/(hr.ft ² .°F)	18.01 W/(m.K)	E 1461-92

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 18000 psi	69 - 124 MPa
Melt Temperature	540 - 580 °F	282 - 304 °C
Mold Temperature	200 - 300 °F	93 - 149 °C
Drying	4 hrs @ 175 °F	4 hrs @ 79 °C
Moisture Content	0.20 %	0.20 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

Desiccant Type Dryer Required.