



**Product Data Sheet &  
General Processing Conditions**

**RTP 299 X 146804 A  
Nylon 6/6 (PA)  
Glass Bubbles  
Preliminary Datasheet**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Specific Gravity	0.82	0.82	D 792
<b>MECHANICAL</b>			
Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	0.3 ft-lbs/in	16 J/m	D 256
unnotched 1/8 in (3.2 mm) section	3.0 ft-lbs/in	160 J/m	D 4812
Tensile Strength	6750 psi	47 MPa	D 638
Tensile Elongation	1.0 - 2.0 %	1.0 - 2.0 %	D 638
Tensile Modulus	0.53 x 10 <sup>6</sup> psi	3654 MPa	D 638
Flexural Strength	9500 psi	66 MPa	D 790
Flexural Modulus	0.52 x 10 <sup>6</sup> psi	3585 MPa	D 790
<b>THERMAL</b>			
Ignition Resistance*			
Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.  
 Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.  
 \* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.  
 \*\* Values per RTP Company testing.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 18000 psi	69 - 124 MPa
Melt Temperature	530 - 570 °F	277 - 299 °C
Mold Temperature	150 - 225 °F	66 - 107 °C
Drying	4 hrs @ 175 °F	4 hrs @ 79 °C
Moisture Content	0.20 %	0.20 %
Dew Point	0 °F	-18 °C

**PROCESSING NOTES**

Desiccant Type Dryer Required.