



**Product Data Sheet &
General Processing Conditions**

**RTP 299 X 93636 B
Nylon 6/6 (PA)
Wear Resistant**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.17	1.17	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0200 - 0.0350 in/in	2.00 - 3.50 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.2 ft-lbs/in	64 J/m	D 256
unnotched 1/8 in (3.2 mm) section	23.0 ft-lbs/in	1228 J/m	D 4812
Tensile Strength	10500 psi	72 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.30 x 10 ⁶ psi	2068 MPa	D 638
Flexural Strength	15500 psi	107 MPa	D 790
Flexural Modulus	0.40 x 10 ⁶ psi	2758 MPa	D 790

ELECTRICAL

Volume Resistivity	1E14 - 1E16 ohm.cm	1E14 - 1E16 ohm.cm	D 257
--------------------	--------------------	--------------------	-------

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	180 °F	82 °C	D 648
Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 18000 psi	69 - 124 MPa
Melt Temperature	530 - 570 °F	277 - 299 °C
Mold Temperature	150 - 225 °F	66 - 107 °C
Drying	4 hrs @ 175 °F	4 hrs @ 79 °C
Moisture Content	0.20 %	0.20 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

Desiccant Type Dryer Required.