




**Product Data Sheet &
General Processing Conditions**

**EMI 330 D FR
Polycarbonate (PC)
Stainless Steel Fiber
Electrically Conductive
EMI/RFI/ESD Protection
Flame Retardant**



PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	8 %	8 %	
Specific Gravity	1.35	1.35	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0060 - 0.0070 in/in	0.60 - 0.70 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.3 ft-lbs/in	69 J/m	D 256
unnotched 1/8 in (3.2 mm) section	18.0 ft-lbs/in	961 J/m	D 4812
Tensile Strength	9300 psi	64 MPa	D 638
Tensile Elongation	5.0 - 8.0 %	5.0 - 8.0 %	D 638
Tensile Modulus	0.42 x 10 ⁶ psi	2896 MPa	D 638
Flexural Strength	9300 psi	64 MPa	D 790
Flexural Modulus	0.42 x 10 ⁶ psi	2896 MPa	D 790

ELECTRICAL

Volume Resistivity	< 100 ohm.cm	< 100 ohm.cm	D 257
Surface Resistivity	< 1E5 ohm/sq	< 1E5 ohm/sq	D 257
Surface Resistance	< 1E4 ohm	< 1E4 ohm	ESD STM11.11
Static Decay MIL-PRF-81705D, 5kV to 50 V, 12% RH	< 2.00 s	< 2.00 s	FTMS101C 4046.1

THERMAL

Ignition Resistance* Flammability	V-0 @ 1/16 in	V-0 @ 1.5 mm	UL94
--------------------------------------	---------------	--------------	------

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.
* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	530 - 580 °F	277 - 304 °C
Mold Temperature	160 - 250 °F	71 - 121 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-20 °F	-29 °C