



**Product Data Sheet &
General Processing Conditions**

**RTP 302
Polycarbonate (PC)
Glass Fiber**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	15 %	15 %	
Specific Gravity	1.29	1.29	D 792
Melt Flow Rate @ 300 °C, / 1.2 kg	7.00 - 12.00 g/10 min	7.00 - 12.00 g/10 min	D 1238
Molding Shrinkage 1/8 in (3.2 mm) section	0.0020 - 0.0040 in/in	0.20 - 0.40 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	2.0 ft-lbs/in	107 J/m	D 256
unnotched 1/8 in (3.2 mm) section	16.0 ft-lbs/in	854 J/m	D 4812
Tensile Strength	13500 psi	93 MPa	D 638
Tensile Elongation	3.0 - 5.5 %	3.0 - 5.5 %	D 638
Tensile Modulus	0.70 x 10 ⁶ psi	4826 MPa	D 638
Flexural Strength	20500 psi	141 MPa	D 790
Flexural Modulus	0.65 x 10 ⁶ psi	4482 MPa	D 790

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	280 °F	138 °C	D 648
Ignition Resistance*			
Flammability**	V-2 @ 1/16 in	V-2 @ 1.5 mm	D 3801
Flammability**	V-1 @ 1/8 in	V-1 @ 3.0 mm	D 3801

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	550 - 600 °F	288 - 316 °C
Mold Temperature	180 - 250 °F	82 - 121 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-20 °F	-29 °C

PROCESSING NOTES

Desiccant Type Dryer Required.