



**Product Data Sheet &
General Processing Conditions**

**RTP 383 HEC
Polycarbonate (PC)
Nickel-Coated Carbon Fiber
EMI/RFI Shielding
Electrically Conductive**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	20 %	20 %	
Specific Gravity	1.33	1.33	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0010 - 0.0020 in/in	0.10 - 0.20 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.3 ft-lbs/in	69 J/m	D 256
unnotched 1/8 in (3.2 mm) section	10.0 ft-lbs/in	534 J/m	D 4812
Tensile Strength	19500 psi	134 MPa	D 638
Tensile Elongation	2.3 %	2.3 %	D 638
Tensile Modulus	1.40 x 10 ⁶ psi	9653 MPa	D 638
Flexural Strength	27500 psi	190 MPa	D 790
Flexural Modulus	1.30 x 10 ⁶ psi	8964 MPa	D 790

ELECTRICAL

Volume Resistivity	< 1E0 ohm.cm	< 1E0 ohm.cm	D 257
Surface Resistivity	< 1E4 ohm/sq	< 1E4 ohm/sq	D 257
Surface Resistance	< 1E3 ohm	< 1E3 ohm	ESD STM11.11
Static Decay MIL-PRF-81705D, 5kV to 50 V, 12% RH	< 0.50 s	< 0.50 s	FTMS101C 4046.1

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	288 °F	142 °C	D 648
--	--------	--------	-------

EMI

Shielding Effectiveness @ 2 mm thickness	75 dB @ 300 MHz	75 dB @ 300 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	79 dB @ 500 MHz	79 dB @ 500 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	83 dB @ 700 MHz	83 dB @ 700 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	86 dB @ 1000 MHz	86 dB @ 1000 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	88 dB @ 1300 MHz	88 dB @ 1300 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	91 dB @ 1500 MHz	91 dB @ 1500 MHz	D 4935

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	550 - 600 °F	288 - 316 °C
Mold Temperature	180 - 250 °F	82 - 121 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C

Moisture Content
Dew Point

0.02 %
-20 °F

0.02 %
-29 °C

PROCESSING NOTES

Remove hopper magnets.
Desiccant Type Dryer Required.