



**Product Data Sheet &  
General Processing Conditions**

**PermaStat PLUS® 2500 A  
Polycarbonate/ABS Alloy (PC/ABS)  
Permanently Static Dissipative  
ESD Protection**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Specific Gravity	1.14	1.14	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0060 - 0.0080 in/in	0.60 - 0.80 %	D 955
<b>MECHANICAL</b>			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	22.0 ft-lbs/in	1175 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	6700 psi	46 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.26 x 10 <sup>6</sup> psi	1793 MPa	D 638
Flexural Strength	11000 psi	76 MPa	D 790
Flexural Modulus	0.30 x 10 <sup>6</sup> psi	2068 MPa	D 790
<b>ELECTRICAL</b>			
Volume Resistivity	1E7 - 9.9E8 ohm.cm	1E7 - 9.9E8 ohm.cm	D 257
Surface Resistivity	1E8 - 9.9E9 ohm/sq	1E8 - 9.9E9 ohm/sq	D 257
Surface Resistance	1E7 - 9.9E8 ohm	1E7 - 9.9E8 ohm	ESD STM11.11
Static Decay	< 0.50 s	< 0.50 s	FTMS101C 4046.1

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.  
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	420 - 480 °F	216 - 249 °C
Mold Temperature	125 - 175 °F	52 - 79 °C
Drying	4 hrs @ 200 °F	4 hrs @ 93 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-20 °F	-29 °C

**PROCESSING NOTES**

Do not exceed 520 °F (270 °C) melt temperature.  
Desiccant Type Dryer Required.