



**Product Data Sheet &
General Processing Conditions**

RTP 2599 X 61232 A FR
Polycarbonate/ABS Alloy (PC/ABS)
PTFE Lubricated
Flame Retardant
Bromine/Chlorine Free
UL94 V-0



PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.22	1.22	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0040 - 0.0060 in/in	0.40 - 0.60 %	D 955
Water Absorption, 24 hrs @ 23°C	0.150 %	0.150 %	D 570
MECHANICAL			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	4.0 ft-lbs/in	214 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	7500 psi	52 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.36 x 10 ⁶ psi	2482 MPa	D 638
Flexural Strength	13000 psi	90 MPa	D 790
Flexural Modulus	0.36 x 10 ⁶ psi	2482 MPa	D 790
Hardness Rockwell, R	116	116	D 785
ELECTRICAL			
Volume Resistivity	> 1E16 ohm.cm	> 1E16 ohm.cm	D 257
THERMAL			
Deflection Temperature @ 264 psi (1820 kPa)	205 °F	96 °C	D 648
@ 66 psi (455 kPa)	215 °F	102 °C	D 648
Ignition Resistance* Flammability	V-0 @ 1/16 in	V-0 @ 1.5 mm	UL94

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
 Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.
 * This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	470 - 525 °F	243 - 274 °C
Mold Temperature	125 - 200 °F	52 - 93 °C
Drying	4 hrs @ 200 °F	4 hrs @ 93 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-20 °F	-29 °C