



**Product Data Sheet &  
General Processing Conditions**

**RTP 2205 LF  
Polyetheretherketone (PEEK)  
Glass Fiber  
Low Flow**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Primary Additive	30 %	30 %	
Specific Gravity	1.52	1.52	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0030 in/in	0.30 %	D 955

**MECHANICAL**

Impact Strength, Izod notched 1/8 in (3.2 mm) section	2.2 ft-lbs/in	117 J/m	D 256
unnotched 1/8 in (3.2 mm) section	17.0 ft-lbs/in	908 J/m	D 4812
Tensile Strength	25000 psi	172 MPa	D 638
Tensile Elongation	2.5 %	2.5 %	D 638
Tensile Modulus	1.70 x 10 <sup>6</sup> psi	11722 MPa	D 638
Flexural Strength	37000 psi	255 MPa	D 790
Flexural Modulus	1.60 x 10 <sup>6</sup> psi	11032 MPa	D 790

**THERMAL**

Deflection Temperature @ 264 psi (1820 kPa)	600 °F	316 °C	D 648
Ignition Resistance* Flammability**	V-0 @ 1/16 in	V-0 @ 1.5 mm	D 3801

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

\*\* Values per RTP Company testing.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	12000 - 18000 psi	83 - 124 MPa
Melt Temperature	660 - 750 °F	349 - 399 °C
Mold Temperature	325 - 425 °F	163 - 218 °C
Drying	3 hrs @ 300 °F	3 hrs @ 149 °C
Moisture Content	0.10 %	0.10 %
Dew Point	-20 °F	-29 °C

**PROCESSING NOTES**

Desiccant Type Dryer Required.