



**Product Data Sheet &
General Processing Conditions**

**EMI 2160.5
Polyetherimide (PEI)
Stainless Steel Fiber
Electrically Conductive
EMI/RFI/ESD Protection**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	5 %	5 %	
Specific Gravity	1.33	1.33	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0060 - 0.0080 in/in	0.60 - 0.80 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.0 ft-lbs/in	53 J/m	D 256
unnotched 1/8 in (3.2 mm) section	10.0 ft-lbs/in	534 J/m	D 4812
Tensile Strength	14000 psi	97 MPa	D 638
Tensile Elongation	8.0 - 12.0 %	8.0 - 12.0 %	D 638
Tensile Modulus	0.52 x 10 ⁶ psi	3585 MPa	D 638
Flexural Strength	20000 psi	138 MPa	D 790
Flexural Modulus	0.50 x 10 ⁶ psi	3448 MPa	D 790

ELECTRICAL

Volume Resistivity	< 1E2 ohm.cm	< 1E2 ohm.cm	D 257
Surface Resistivity	< 1E6 ohm/sq	< 1E6 ohm/sq	D 257
Surface Resistance	< 1E5 ohm	< 1E5 ohm	ESD STM11.11
Static Decay MIL-PRF-81705D, 5kV to 50 V, 12% RH	< 2.00 s	< 2.00 s	FTMS101C 4046.1

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	12000 - 18000 psi	83 - 124 MPa
Melt Temperature	670 - 750 °F	354 - 399 °C
Mold Temperature	275 - 350 °F	135 - 177 °C
Drying	4 hrs @ 300 °F	4 hrs @ 149 °C
Moisture Content	0.04 %	0.04 %
Dew Point	-20 °F	-29 °C