



**Product Data Sheet &
General Processing Conditions**

**RTP 2105
Polyetherimide (PEI)
Glass Fiber**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	30 %	30 %	
Specific Gravity	1.50	1.50	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0020 in/in	0.20 %	D 955
Water Absorption, 24 hrs @ 23°C	0.180 %	0.180 %	D 570
MECHANICAL			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.6 ft-lbs/in	85 J/m	D 256
unnotched 1/8 in (3.2 mm) section	12.8 ft-lbs/in	683 J/m	D 4812
Tensile Strength	25100 psi	173 MPa	D 638
Tensile Elongation	2.6 %	2.6 %	D 638
Tensile Modulus	1.55 x 10 ⁶ psi	10687 MPa	D 638
Flexural Strength	35700 psi	246 MPa	D 790
Flexural Modulus	1.45 x 10 ⁶ psi	9998 MPa	D 790
Hardness Rockwell, R	123	123	D 785
ELECTRICAL			
Dielectric Strength, S/T, in oil	500 VPM	19.7 kV/mm	D 149
Dielectric Constant, 1 MHz, Dry	3.9	3.9	D 150
Dissipation Factor, 1 MHz, Dry	0.0050	0.0050	D 150
Volume Resistivity	> 1E12 ohm.cm	> 1E12 ohm.cm	D 257
THERMAL			
Deflection Temperature @ 264 psi (1820 kPa)	405 °F	207 °C	D 648
@ 66 psi (455 kPa)	410 °F	210 °C	D 648
Ignition Resistance* Flammability**	V-0 @ 1/16 in	V-0 @ 1.5 mm	D 3801
Coefficient of Linear Thermal Expansion Flow Direction	1.2 x 10 ⁻⁵ /°F	2.2 x 10 ⁻⁵ /°C	E 831
Thermal Conductivity Through-plane	1.80 (BTU.in)/(hr.ft ² .°F)	0.26 W/(m.K)	E 1530

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	12000 - 18000 psi	83 - 124 MPa
Melt Temperature	670 - 750 °F	354 - 399 °C
Mold Temperature	275 - 350 °F	135 - 177 °C
Drying	4 hrs @ 300 °F	4 hrs @ 149 °C
Moisture Content	0.04 %	0.04 %
Dew Point	-20 °F	-29 °C