



**Product Data Sheet &
General Processing Conditions**

**RTP 4105
Polyetherketoneketone (PEKK)
Glass Fiber**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	30 %	30 %	
Specific Gravity	1.51	1.51	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0030 in/in	0.30 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.6 ft-lbs/in	85 J/m	D 256
unnotched 1/8 in (3.2 mm) section	15.0 ft-lbs/in	801 J/m	D 4812
Tensile Strength	25500 psi	176 MPa	D 638
Tensile Elongation	2.0 %	2.0 %	D 638
Tensile Modulus	1.70 x 10 ⁶ psi	11722 MPa	D 638
Flexural Strength	38000 psi	262 MPa	D 790
Flexural Modulus	1.60 x 10 ⁶ psi	11032 MPa	D 790

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	> 600 °F	> 316 °C	D 648
Ignition Resistance* Flammability**	V-0 @ 1/16 in	V-0 @ 1.5 mm	D 3801

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	15000 - 20000 psi	103 - 138 MPa
Melt Temperature	710 - 720 °F	377 - 382 °C
Mold Temperature	300 - 450 °F	149 - 232 °C
Drying	3 hrs @ 300 °F	3 hrs @ 149 °C
Moisture Content	0.10 %	0.10 %
Dew Point	-20 °F	-29 °C

PROCESSING NOTES

Desiccant Type Dryer Required.